

FLUTESTAR PLUS



Description

This product specifically targets the market sector where **performance** is of the **very highest priority**.

The mechanical properties of this product, **manufactured exclusively using recovered fibre**, compares favourably with “European” style semi-chemical flutings and their substitutes.

It performs particularly well in highly demanding and difficult environments, such as those with a high static charge, high humidity and low temperatures.

This **product** has **proved** itself in a large number of tests in the most exacting conditions.

Product Grammage Range and Specification

Nominal	115	127	135	140	150	160	170
SCT (kN/m)	2.35	2.70	2.95	3.10	3.35	3.50	3.80
CMT (N)	210	265	300	310	330	347	375

Mini	115	127	135	140	150	160	170
SCT (kN/m)	2.15	2.50	2.65	2.75	3	3.17	3.35
CMT (N)	200	245	270	280	290	305	330

Standard atmospheric laboratory conditions, as specified in : NF EN 20 187
Reel moisture content: 8.5 % +/- 1.5 – ISO 287