

ONDULSTAR



Description

The mechanical performance of this, **100% recycled paper**, allows its utilisation **to optimise**, not only **board grades** but also **pack design**; for a complete packaging solution cost optimisation. This product can be utilised in the **majority** of corrugated applications.

Product Grammage Range and Specification

Nominal	105	110	115	120	125	130	135
SCT (kN/m)	1.86	1.92	2.00	2.08	2.15	2.23	2.30
CMT (N)	180	180	200	210	215	220	230

Mini	105	110	115	120	125	130	135
SCT (kN/m)	1.70	1.75	1.80	1.90	2.00	2.08	2.15
CMT (N)	160	170	180	190	195	200	213

Nominal	140	150	155	160	170	190
SCT (kN/m)	2.40	2.60	2.70	2.80	3.05	3.42
CMT (N)	245	265	273	280	325	

Mini	140	150	155	160	170	190
SCT (kN/m)	2.24	2.40	2.48	2.60	2.72	3.20
CMT (N)	225	245	252	260	280	

Standard atmospheric laboratory conditions, as specified in : NF EN 20 187
Reel moisture content: 8.5 % +/- 1.5 – ISO 287