

Description

This product combines the performance of a waste based fluting with the appearance of a testliner. The principal objective of this product is to assist the corrugator to **optimise reel stock** and **rationalise corrugated board grades**.

An innovative and economic approach to help solve your problems !

Product Grammage Range and Specification

Nominal	90	95	100	105	110	115	120
SCT (kN/m)	1.70	1.75	1.80	1.86	1.92	2.00	2.08
Burst (kPa)	215	225	230	240	270	280	290
CMT (N)	150	160	170	180	190	200	215

Mini	90	95	100	105	110	115	120
SCT (kN/m)	1.55	1.60	1.65	1.70	1.75	1.80	1.90
Burst (kPa)	190	200	205	215	225	235	240
CMT (N)	130	140	150	160	170	180	190

Nominal	125	130	140	150	165	170	200
SCT (kN/m)	2.15	2.23	2.40	2.60	2.90	3.05	3.50
Burst (kPa)	300	310	320	355	375	390	460
CMT (N)	225	240	255	285	290	325	

Mini	125	130	140	150	165	170	200
SCT (kN/m)	2.00	2.08	2.24	2.40	2.64	2.72	3.35
Burst (kPa)	255	275	300	330	355	365	450
CMT (N)	195	200	225	245	272	280	

Standard atmospheric laboratory conditions, as specified in : NF EN 20 187
Reel moisture content: 8.5 % +/- 1.5 – ISO 287

Standard atmospheric laboratory conditions, as specified in : NF EN 20 187
Reel moisture content: 8.5 % +/- 1.5 – ISO 287